



Customer:

AS Uninaks

Forelli11  
10612 TALLINN

02.05.2022

**Experimental Report N° 245/22**

Page 1/1

Assignment: Testing of mortar for masonry.

Product designation: Dry mix of mortar for masonry, marked as „Naks M 100, 01.03.22, liin 07”.

Forwarded to the laboratory by customer on 24.03.2022 (25 kg).

Test method: EN 1015 „Methods of test for mortar for masonry”.

Fresh mortar was prepared in accordance with EN 1015-2 using water quantity, specified by manufacturer  $w = 0.17$ . Mortar was mixed in mixer according to EVS-EN 196-1 and the following mixing procedure: mixing 1,5 min + maturing time 3 min + mixing 1 min. The flow value was determined in accordance with EN 1015-3 and it was **172 mm**. For determination of the compressive strength of hardened mortar, three test specimens with dimensions 40x40x160 mm were prepared according to EN 1015-11. Test specimens were cured: at temperature  $(20 \pm 2) ^\circ\text{C}$  and relative humidity  $(95 \pm 5) \%$  2 days in the mould and 5 days with the mould removed and after that at temperature  $(20 \pm 2) ^\circ\text{C}$  and relative humidity  $(65 \pm 5) \%$  21 days with the mould removed. For compressive strength test specimens were broken into two halves to provide six half prisms. The compressive strength was determined in accordance with EN 1015-11. The results are given in next table.

Test results:

Preparing date	Testing date	Age, days	Compressive strength, N/mm <sup>2</sup>		
			individual		mean
04.04.22	02.05.22	28	16,00	15,40	15,7
			15,30	15,75	
			15,30	16,20	

The test results are valid to the described test sample only.

(signed digitally)

Margit Rosenberg  
Technology Engineer

The experimental report can be copied only as a whole; the laboratory must give its permission for partial copying.