

NAKS-2

HIGH-QUALITY TILE ADHESIVE

USAGE

- For installing ceramic, clinker and stone tiles on stone,
- plaster, concrete and other hard surfaces.
- For installing tiles on old tiles. For tiling
- pools, especially in wet rooms and hot environments.
- For installing wall and floor tiles.
- Also suitable for installing tiles outside.

MIXING

- Pour mixture into a mixer or a bowl with a wide opening.
- Add water approx. 20- 22% of the weight of the mixture
- (5-5.5 l per 25 kg package or 1-1.1 l per 5 kg box).
- Mix carefully.
- Before installing tiles wait 10 minutes.
- Ready mixture to be used within 6 hours after adding water.

INSTALLATION

- Apply mixture onto wall with a special toothed spatula.
- Or apply mixture onto individual tiles with a spatula and thereafter install tiles
- on the wall.
- The thickness of the mixture layer applied onto wall is normally 0.5-2 mm.
- Tiles to be pressed on the mixture within 30 minutes after the mixture has been applied on the surface.

CURING

- The installed tiles are ready for jointing works in 24 hours.
- The tiled surfaces reach final strength similar to the test strength in 12 days.

LIMITATIONS

- The temperature of the mix and substrate must be over +5° C.
- Restrict traffic for 3 days.

STORAGE

- Storage time of the mix powder is 1 year.
- Mix packed in bags or boxes should be stored in a dry room.

CONSUMPTION

- Consumption of the mixture for installing 1 m² of tiles is 3-4 kg, depending on the substrate and thickness of the layer.