

27-400 Ostrowiec Św.

ul. Żabia 35

NIP 661-23-55-950

TECHNICAL DATA SHEET

SPECIES AS	PARAMETERS
Chemical analysis	
Al₂O₃ min	% 36,0
Fe₂O₃ max	% 3,0
Apparent density min	g/cm³ 2,0
Normal refractoriness min	sP 171/173
Open porosity max	% 22
Compressive strenght min	MPa 20
Refractoriness under load t_{0,6} min	°C 1370

